

SPECIFICATIONS

<u>PRODUCT</u>	SOAP STONE POWDER
Rates in INR Per Tonne:	2700 To 12500
Particle Size:	200 to 1250 mesh
State:	Powder
Whiteness:	81% to 97%
Brightness:	78% to 96%
Purity:	99 %
Silica as SiO2:	62%
Magnesium Carbonate as MgCo3:	31%
Alumunium Oxide as Al2O3:	4%
Ferrous Oxide as Fe2O3:	1.40%
Calcium oxide as CaO:	1.50%
Magnesium Oxide as MgO:	0.3
CaCl2:	1-0.32
Other Oxides	1.50%
Appearance/Color:	white
Molecular Formula:	C27H44O3
Grade Standard:	Industrial Grade
pH Value:	8.5-9.3
Refractive index:	nα = 1.538 – 1.550
Specific Gravity:	nβ = 1.589 – 1.594
Loss on ignition:	6%
Moisture:	0.5
Solubility:	nγ = 1.589 – 1.600
Hardness:	1 Mohs

Water Absorption:	30-35%
Surface Area:	3 - 6 m2/gm
Ash:	3%
Crystal habit:	Foliated to fibrous masses, rare as platey to pyramidal crystals
Crystal system:	Monoclinic or triclinic[2]
Cleavage:	Perfect on {001} basal cleavage
Fracture:	Flat surfaces (not cleavage), fracture in an uneven pattern
Tenacity:	Sectile
Luster:	Waxlike or pearly
Streak:	White to pearl green
Diaphaneity:	Translucent
Optical properties:	Biaxial (-)
Birefringence:	δ = 0.051
Pleochroism:	Weak in dark varieties
Ultraviolet fluorescence:	Short UV=orange yellow, long UV=yellow
Odor:	Odorless
Lumps:	Yes
	1

GALAXY GLOBAL

Phone:9560734700 || 9205664610,

E - Mail: galaxyglobalminerals@gmail.com

Website: www.galaxyglobal.in

Head Office: 43, Apna Shalimar, Alwar, Rajasthan, 301001 Corporate Office: 16, E1.1, Vatika INXT, Sector 82, Gurugram, NCR

OUR PRODUCTS:

DOLOMITE || CALCITE || SOAP STONE || CHINA CLAY || CALCIUM CHLORIDE || CALCIUM CARBONATE || MARBLE CHIPS