

Wasser Polymer Pvt. Ltd

POLYCOAT- 6020

P.U Matte Finish



TDS/PU6020 /020513

Technical Data Sheet

Product Description:

Two component, air drying, acrylic aliphatic polyurethane matt coating.

Features :

- Finish coat on epoxy and polyurethane systems.
- Ideal for coastal and industrially polluted exposure conditions.
- Very good abrasion resistance
- Resistance to splash & spillage of water/saline water and mild chemicals.

Technical

Details :

Color	: Range 25 shades.
Gloss	: Matt - Eggshell
Volume solids	: Approx.
50% Recommended DFT / coat	: 35 - 50 μ
Theoretical covering capacity	: 10 to 15 m^2/l @ 35 μ
DFT	
Curing time at 30°C	: Surface dry : 1 hour
	: Hard dry : 8 hours
	: Full cure : 7 days
Shelf life (cool & dry place)	: 6 months(min)
Flash point	: Base : < 28°C
	: Hardener : < 28°C

Surface Preparation & Substrate Condition	<p>Can be applied on epoxy primer, epoxy /polyurethane undercoat; surface must be dry & free from all surface contamination. Surface of aged epoxy coating should be sufficiently roughened prior to painting.</p> <p>Substrate temperature should be at least 3°C above dew point but not above 50°C.</p>
Mixing:	<p>Stir the base and hardener separately to get an uniform mix, then add hardener slowly to the base slowly with constant stirring for quick homogenous mixing.</p> <ol style="list-style-type: none"> 1. Mixing ratio : Base : Hardener :: 10:1(v/v) 2. Induction time : 25 minutes 3. Pot life at 30° : 3 hours
Application:	<p>Brush</p> <ol style="list-style-type: none"> 1. Recommended thinner : Vib Thinner No. 9 2. Volume of thinner : 0 - 10 % <p>Air spray</p> <ol style="list-style-type: none"> 1. Recommended thinner : Vib Thinner No. 9. 2. Volume of thinner : 5 - 20 % 3. Nozzle orifice : 1.5 - 3.0 mm 4. Nozzle pressure : 0.3 - 0.4 MPas <p>Airless spray</p> <ol style="list-style-type: none"> 1. Recommended thinner : Vib Thinner No. 9 2. Volume of thinner : 0 - 15 % 3. Nozzle orifice : 0.41 - 0.48 mm 4. Nozzle pressure : 20 - 24 MPas

Disclaimer: *The informations given in this data sheet are true to the best of our knowledge and based on our lab trials and should not be purported to be authentic, as the methods and areas of applications differ. The user should conduct his own trials and applications before using. The manufacturer is not responsible for any loss or damage arising out of the use of the product.*

Office:
66, Paikpara Row
Kolkata 700037
Phone: 9830105859/ 033- 2556-5629
Email: wasserpolymer @gmail.com
May 2, 2013