



GUUDPOLY Liquid Defoamer

Goodyear Grade	Chemistry	Appearance	Viscosity (mpa·s)	Application Stage	Water Dilution	Effect on gloss	speciality	Recommend Application Field
LMM410	Mineral oil	light yellow liquid	500~ 2000	Grinding/mixing	No		Defoam quickly and effective at microbubbles, excellent durability. 30-50% less dosage	Water-borne paints, ink, Adhesives
LMPS190	Mineral oil	light yellow liquid	800~ 2400	Grinding/mixing	Yes		High efficiency, long-lasting performance, suitable for medium to high viscosity	Emulsion Polymerization, Pressure sensitive glue
LMWP5800	Mineral oil	Milky white Emulsion	4000~ 12000	Grinding	No	No	Quickly break foam, long-lasting performance. Cost-	Wall Paints, PVC, Medium to high PVC
LMW681F	Mineral oil	light yellow liquid, opaque	500~ 2500	Grinding/mixing	No	—	General-purpose, works quickly to break foam, good	Water-borne paints
LMW033	Mineral oil	light yellow liquid, opaque	2000~ 5000	Grinding/mixing	No	—	General-purpose, quickly break foam, good compatibility.	Water-borne paints, ink, Adhesives, emulsion polymerization
LMV345	Mineral oil	light yellow liquid, opaque	1000~ 3000	Grinding	No	Low	Strong defoaming ability, no residual microbubbles, very smooth surface.	Elastic, High viscosity paints
LSM56N	Polyorgano siloxane	Milky white liquid	500~ 1500	Grinding	Yes	No	General-purpose, high-efficiency, 100% AC	Water-borne Industrial Paints,Inks
LSPI901	Polyorgano siloxane	Offwhite turbid liquid	50~200	Grinding	Yes	No	High-efficiency, 100% active content	Water-borne Industrial Paints, Inks
LSPI901	Polyorgano siloxane	offwhite liquid, opaque	50~200	Grinding/mixing	Yes	No	No hydrophobic particles, good compatibility	Water-borne Industrial Paints,Inks
LSPI022	Polyorgano siloxane	colorless to translucent liquid	60~300	Grinding	No	No	high-efficiency, 100% active content	Water-borne Industrial Paints, Inksadhesive & Sealent
LSPI028	Polyorgano siloxane	colorless liquid	100~300	Grinding/mixing	No	No	No hydrophobic particles, good compatibility	Water-borne Industrial Paints,Inks
LSEP825	Polyorgano siloxane	Milky white emulsion	—	Grinding/mixing	Yes		Strong defoaming ability, good compatibility.	Water-borne Industrial Paints,Inks
LSEP065	Polyorgano siloxane	Milky white to yellowish emulsion	—	Grinding	Yes		Strong defoaming ability, good compatibility.	Water-borne Industrial Paints,Inks
LSE965	Polyorgano siloxane	Offwhite turbid liquid	1500~ 3000	Grinding	No		Strong defoaming ability,good compatibility. suitable for high-solid-content, high-film-thickness systems.	oil based expoxy flooring paints
LSE966	Polyorgano siloxane	Offwhite turbid liquid	1500~ 3000	Grinding	No		Stronger defoaming ability, suitable for high-solid-content, high-film-thickness solvent-based systems.	oil based expoxy flooring paints, Ink