



PARSHWANATH GROUP OF INDUSTRIES

Plot No. I - 5617, Phase - 2, Vatva, G.I.D.C.
Ahmedabad - 382445, Gujarat, India

Telephone : +(91)-(79)-40083231/40085401/40085400

Email : inquiry@parshwadyes.com

Reactive ME Dye	FASTNESS PROPERTIES				
	Light	Washing	Perspiration	Hypochlorite	Dischargeability
Red ME4BL Red - 195	6	4-5	4-5	3	P
Red ME6BL Red - 196/250	5	4-5	4	3-4	F
Red ME3BL Red - 180	5-6	5	5	1	P
Orange ME2RL Orange - 122	5	5	4	2	P
G. Yellow MERL Yellow - 145	5	5	4	4	F
Yellow ME3RL	6	4-5	4-5	1	F
Yellow ME4GL Yellow-160/186	6	4-5	4-5	1	F
Green ME4GL	4-5	4-5	4	1	F
Blue ME2RL Blue - 158	4	5	4	1	F
Navy Blue ME2GL Blue 194	4-5	4-5	4	1	F
Jet Black HFGR	5-6	5	5	2	F
Black HFGR	4	5	4	3	G
Copper Blue BF Blue - 221	6-7	4	4	2	G
Blue BF Blue - 222	4-5	4	4	2	G