

Sunfast & Non Benzidine Direct Dyes		FASTNESS PROPERTIES				
		Light	Washing	Perspiration	Hypochlorite	Dischargeability
Direct Dyes Yellow 3GX Direct Dyes Yellow - 6		3	2	4	4	F
Direct Dyes Paper Yellow T Direct Dyes Yellow - 11		4	2-3	4	4-5	P
Direct Dyes Crysophine Direct Dyes Yellow - 12		4-5	2	5	2	F
Direct Dyes Yellow 5GLL H/C Direct Dyes Yellow - 44		3	3	1	1	G
Direct Dyes Yellow 5GLL Direct Dyes Yellow - 44		3	3	1	1	P
Direct Dyes Yellow RSLW Direct Dyes Yellow - 50		6	4	5	5	G
Direct Dyes Yellow RL Direct Dyes Yellow - 86		6	4	5	5	G
Direct Dyes Sunfast Yellow RCH Direct Dyes Yellow - 99		4	2-3	4	2-3	F
Direct Dyes Orange SE 200% Direct Dyes Orange - 26		4	4	4-5	4-5	F
Direct Dyes Orange TGLL Direct Dyes Orange - 39		6-7	3	5	2	F
Direct Dyes Orange TGLL 200% Direct Dyes Orange - 39		6-7	3	5	2	F
Direct Dyes Viscose Orange BRO Direct Dyes Orange - 108		2	2	5	5	G
Direct Dyes Scarlet 4BS Direct Dyes Red - 23		3	3-4	4	4	F
Direct Dyes Red 12B Direct Dyes Red - 31		1-2	3	3	3	F
Direct Dyes Light Red BLN Direct Dyes Red - 80		6	3	5	5	F
Direct Dyes Red 5B Direct Dyes Red - 81		4-5	3	4	4	G
Direct Dyes Red 5B 200% Direct Dyes Red - 81		4-5	3	4	4	G
Direct Dyes Violet MB Direct Dyes Violet - 9		2-3	2	5	5	G
Direct Dyes Brill Violet HELIO B Direct Dyes Violet - 51		2-3	2	5	5	G
Direct Dyes Sky Blue FBC Direct Dyes Blue - 1		2	3-4	5	5	F
Direct Dyes Sky Blue FFH Direct Dyes Blue - 15		2	3-4	5	5	F
Direct Dyes Blue JJR Direct Dyes Blue - 67		4	3	4	4	P
Direct Dyes Blue GLL Direct Dyes Blue - 71		5	3-4	5	5	F
Direct Dyes Blue GLL 200% Direct Dyes Blue - 71		5	3-4	5	5	F
Direct Dyes Fast Blue RLL Direct Dyes Blue - 80		6	3	5	5	G
Direct Dyes Tur. Blue SBL Direct Dyes Blue - 86		6-7	4	5	1	F
Direct Dyes Fast Tur. Blue FBL Direct Dyes Blue - 199		4	3-4	4	4	F
Direct Dyes Green JJR Direct Dyes Green - 26		5	3-4	5	5	F
Direct Dyes Green NB Direct Dyes Green - 96		5	3-4	5	5	F
Direct Dyes Black GR Direct Dyes Black - 22		2	3	4	4	G
Direct Dyes Diazo Black OB Direct Dyes Black - 80		2	3	3	4	G
Direct Dyes Diazo Black BF Direct Dyes Black - 155		2	3-4	4	4	G
Direct Dyes Gray 2RL		4	3	4-5	4-5	F
Direct Dyes Brown 2GL		5-6	3	3	3	F