

Product Description

TechnoCrete AEA is a chloride free air entraining admixture based on neutralised Polymeric resin. It is supplied as a translucent water white coloured solution which instantly disperses in water.

TechnoCrete AEA acts at the interface between the mixing water and cement/aggregate particles to produce microscopic air bubbles, which are evenly distributed throughout the concrete.

The entrained air enhances durability by providing protection against the rapid temperature changes found in freezing and thawing conditions and with the use of de-icing salts.

Standard:

TechnoCrete AEA complies with BS 5075 Part 2, BS 4887 Part 1, ASTM C260 and with the Department of Transport Specification for Highway Works.

Uses

- To produce air entrained concrete for increased durability and resistance to damage by frost and deicing salts. Typical applications include concrete roads and bridge decks, airport runways and taxiways and other extensive areas of concrete exposed to potential frost damage.
- To improve cohesion and workability of concrete mixes where poorly graded aggregates must be used and bleeding, segregation or sand runs occur.
- As part of a combined admixture system for the production of ready mixed retarded mortar.

Advantages

- Air entrainment increases the resistance of concrete to attack by frost and de-icing salts, reducing problems of surface scaling and concrete failure.
- Entrained air bubbles assist in the formation of a stable cohesive mix, reducing segregation and bleeding.
- Air entrainment improves workability and helps produce a dense, uniform, close textured surface free from gravel nests and sand runs, so further enhancing durability.
- Excellent air bubble stability allows use with a wide range of aggregate qualities and mix conditions.

Technical Properties

Form	Translucent coloured liquid
Chemical Basis	Modified Polymeric Resin
Specific Gravity	1.16 (at 27°C)
Chloride Content	Nil to BS 5075
Alkali Content	Typically less than 14.0g Na ₂ O equivalent/litre of admixture
pH	Minimum 6

Factors affecting air entrainment:

Sand content: The quantity of air entrained will increase with increasing sand content - typically an increase in sand content from 35 to 45% will raise the air content from 4.5 to 6.0%.

Cement fineness and content: The amount of air entrained reduces with an increase in cement fineness or content.

Aggregate quality: Silt content variations can adversely affect the degree of air entrainment. This is particularly relevant to the use of crushed aggregate during inclement weather.

Excessive silt content may render TechnoCrete AEA ineffective.

Concrete temperature:

A temperature increase will reduce air content. In practice, daily fluctuations are much smaller and do not cause significant variation.

Mixing and pumping:

Air content will increase with increased time of mixing up to about two minutes in stationary mixers and about 15 minutes in transit mixers. Thereafter, the air content generally remains constant for a considerable period. Small losses of air may occur during pumping. With long pipelines, air content in excess of 5% may seriously reduce the efficiency of the pump.

Compaction of concrete:

Prolonged vibration should be avoided. For specific technical assistance and advice on any of the above aspects.

Setting time:

Negligible effect at normal dosage rate.

Compatibility:

TechnoCrete AEA can be used with all types of Portland cements and is generally compatible with other admixtures. It is recommended that all admixtures be added to concrete separately.

Reduced permeability:

The microscopic air bubbles introduced by use of Techno Addplast AEA break up the capillary structure within concrete and hence reduce water permeability.

Durability:

Reducing the water permeability of concrete offers increased resistance to weather exposure and attack in aggressive environments.

Frost resistance:

The addition of TechnoCrete AEA produces controlled air space.

Compressive strength:

15% free water reduction is often possible with TechnoCrete AEA. This resultant increased compressive strength normally offsets the anticipated strength loss associated with air entrainment, thus producing air entrained concrete with no increase in cement content.

Resistance to salts:

Air entrainment increases the resistance of concrete to surface scaling, which is an adverse effect associated with repeated exposure to marine salts or application of de-icing salts to the concrete surface.

Application Instructions

Typical dosage

The optimum dosage of TechnoCrete AEA to meet specific requirements must always be determined by trials using the materials and conditions that will be experienced in use. This allows the optimisation of admixture dosage and mix design and provides a complete assessment of the concrete mix use of de-icing salts.

As a starting point for trials a dosage of 0.08 litres/100kg of cement will typically give an air content of 5% + 1.5% in a medium workability concrete of 300 - 350kg/m³ cementitious content. Where cement replacement materials are used they should be included in the cementitious content for purposes of calculating admixture dosage. The presence of PFA or microsilica may increase the dosage required to obtain a particular air content.

Use at other dosages

Dosages outside the typical ranges suggested on this sheet may be used if necessary and suitable to meet particular mix requirements, provided that adequate supervision is available. Compliance with requirements must be assessed through trial mixes.

Compatibility

TechnoCrete AEA is compatible with other. All admixtures should be added to the concrete separately and must not be mixed together prior to addition. The resultant properties of concrete containing more than one admixture should be assessed by the trial mix.

TechnoCrete AEA is suitable for use with all types of ordinary portland cement.

Dispensing

The correct quantity of Techno Crete AEA should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results.

Curing

As with all structural concrete, good curing practice should be maintained. Water spray, wet hessian spray applied curing membranes should be used.

Cleaning

Spillages of TechnoCrete AEA can be removed with water.

Overdosing

An overdose of double the recommended measure of TechnoCrete AEA will increase workability and air content and can result in slight set retardation of the concrete. The ultimate strength of the concrete should not be impaired if advantage is taken of the water reduction and the concrete is adequately cured.

Estimating

Packaging

TechnoCrete AEA is supplied in 5, 20 and 200 litre carboys.

Storage

TechnoCrete AEA has a minimum shelf life of 12 months in unopened containers under normal warehouse conditions.

Health & Safety

TechnoCrete AEA is non-toxic. Any splashes should be rinsed thoroughly with water. Splashes to the eyes should be washed immediately with water and medical advice should be sought.

Fire

TechnoCrete AEA is non flammable.

Additional information

The Technokem range of associated products includes high strength cementitious, epoxy grout, polyester resin based mortar for rapid pre-setting of steel shims to level or for direct bedding of small base plates; Resin anchoring systems for same day anchoring of bolts in drilled holes in concrete or rock.

Also available range of products for use in construction i.e., admixtures, curing compounds, release agents, flooring systems and repair mortars.

Important: Technokem products are guaranteed against defective materials and are sold subject to its standard terms and conditions of sale. It is the Customer's responsibility to satisfy themselves by checking with the Company whether the information is still current at the time of use. The customer must be satisfied that the product is suitable for the use intended. All products comply with the properties shown on current Technical Literatures. However, Technokem does not warranty or guarantee the installation of the products as it does not have any control over installation or end use of the product. All information and particularly the recommendation relating to application and end use are given in good faith.

For Complaints/Suggestions:

Please write to our Customer Care Executive at

TechnoKem Manufactures of Construction Chemicals

#301, Krishna Classic, Road No.17,

Plot No. 51, Sardar Patel Nagar,

Kukatpally, Hyderabad - 500085,

Off: 040 - 29559256



info@technokem.com

www.technokem.com

An ISO: 9001: 2015 Accredited Company