

(This original only is valid. Third parties who are using copies are doing so at their own risk.)

Project No. TST - 0095

BRIEF EVALUATION REPORT

BS : 476-Part 6 : Method of evaluation for Fire Propagation for Products

Date of Evaluation : May 11- 13, 2015

Sponsor : M/s Shahsahib Wood Wool Enterprises
583, Mukherjee Nagar,
New Delhi – 110 009

Description of Product : **ACUTEX WOODWOOL ACOUSTIC BOARD**
Thickness: 25 mm, Nominal Bulk Density: 400 kg/m³
(Product description has been prepared on the basis of the
information provided by the sponsor).

Specimen dimensions : 225 mm x 225 mm x 25 mm
Results


Number of specimens evaluated : Three


Fire Propagation Index, I : 3.55

Sub-indices : $i_1 = 2.45$, $i_2 = 0.54$, $i_3 = 0.56$

The evaluation results relate only to the behaviour of the specimens of a product under the particular conditions of the evaluation, they are not intended to be the sole criterion for assessing the potential fire hazard of the materials in use.

This report is valid for three years from the date of evaluations of the product.


(RAKESH KUMAR)
CO-INVESTIGATOR


(A. A. ANSARI)
PRINCIPAL INVESTIGATOR



FIRE RESEARCH LABORATORY
CSIR - Central Building Research Institute
Roorkee - 247 667 (U.K.) INDIA

