

# **Technical Data Sheet**

Last revised: 01-2019

## DELTA-DC® 4296

DELTA-DC<sup>®</sup> 4296 is a 100% active wetting and dispersing agent for solvent based coatings and inks.

<b>Specifications:</b> Composition Specific gravity @ 20°C Appearance Active ingredients	<ul> <li>Anionic surface active agent</li> <li>1.03-1.05 g/cm3</li> <li>Yellowish slightly viscous liquid</li> <li>&gt;98%</li> </ul>
<u> </u>	Methods of analysis can be received upon request

#### Applications and usage:

**DELTA-DC® 4296** is suitable to disperse and stabilize fillers, inorganic, organic and carbon black pigments in decorative paints and low-end industrial coatings. **DELTA-DC® 4296** improves the grinding in pigment pastes by allowing good viscosity reduction and increasing the pigment loading. **DELTA-DC® 4296** is particularly suitable for alkyd systems and thermoplastic acrylic based coatings. **DELTA-DC® 4296** should be added prior to pigment grinding **0.1-2.0%** upon total formulation weight (inorganic and organic pigments). The optimum addition level will depend on the specific formulation. Owing to its dual compatibility with low and high polarity systems, **DELTA-DC® 4296** can be effectively used to prepare universal pigment colorants or to be added to alkyd system to improve the acceptance of universal coloring pastes.

### Safety and Handling:

**DELTA-DC®** 4296 should be handled in accordance with good industrial practice. Detailed information can be found in the Safety Data Sheet.

#### Storage:

**DELTA-DC<sup>®</sup> 4296** should be stored at temperatures between 5 °C and 32°C. Although **DELTA-DC<sup>®</sup> 4296** will not freeze under ordinaryconditions, best results can be insured if it is kept between the recommended temperatures prior to use. When kept in an original unopened container, it will keep up to 5 year from the date of manufacture.

### Packaging:

55 kg and 190 kg non-returnable containers.