



BANTHIA MINERAL AND CHEMICAL PVT LTD

PRODUCT :- CHINA CLAY POWDER	REFERENCE NO	
GRADE :- BANTHIA CLAXON 200	MANUFACTURING DT	
D.O.NO :-	PACKAGING	25 kg BAG
NAME OF CUSTOMER:	M/S	
INVOICE NO & DATE	BMCL/EX/	

CHEMICAL ANALYSIS REPORT OF CHINA CLAY POWDER- BANTHIA CLAXON 200

SL. No.	Properties	BANTHIA CLAXON 200
1	Whiteness	75-78 %
2	Shade	White Pinkish
3	Al ₂ O ₃	20-25
4	MgO	0.40
5	SiO ₂	60-65
6	Fe ₂ O ₃	0.05
7	Specific Gravity	2.50
8	LOI	4.20
9	Mesh	200
10	Residue	0.5-1
11	Bulk Density (gm/ml)	0.40-0.55
12	P.H. Value	7-7.5
13	Water Absorption (ml/100 gm)	42-48
14	Mixed Oxides %	1
15	Packing	25 Kg

Prepared By	Checked By	Approved By
Vanraj (Lab-in-Charge)	S.Kothari (Technical)	Binod Kumar Sharma Sr. Manager (Mktg & Sales)

**Regd Office : 76D Harish Chatterjee Street, Opp: Harish Park, Bhawanipur,
BANTHIA [JAIN] HOUSE, Kolkata- 700 025 (W.B) INDIA.
Ph: 033-65352095/24554142/+91-9836068831/9836068832
Email: banthiaindustrialcorp@gmail.com ; info@banthiagroup.net**

Plant : Bijoli Industrial Area, Jhansi (U.P)