

SPECIFICATION

Type – Unsaturated Polyester Resin

Grade – Hason RL (Roof Light)

PROPERTIES OF THE LIQUID RESIN

Sr.	Tests	Result	Method
01	Appearance	Water White	D002
02	Specific Gravity @ 30Deg. C	1.08 $\pm$ 0.02	D001
03	Brookfield @ 25 ° C SP # 2 / 20rpm	200 $\pm$ 300 Cps	D005
04	*Gel Time	8-10 Min	D006
05	Exotherm Peak	160 C - 170 C	D006
06	Styrene Content	42 $\pm$ 2%	D003
07	Acid Value	25 $\pm$ 3 mg/KOH/gm	D004

Material is Pre accelerated *100 gm Resin +0.5 ml Co (6%)+ 1.5 ml MEKP

PROPERTIES OF THE CURED RESIN

1	Tensile Strength	60 $\pm$ 5 Mpa	ISO 527
2	Elongation at break	2-3 %	ISO 527
3	Flexural Strength	90 $\pm$ 10 Mpa	ISO 178
4	Heat Deflection Temperature	75 $\pm$ 5 C	ISO 75(A)
5	Hardness	40 Barcol	ASTM D 2583

HASON CHEMTECH PVT. LTD.
(Formerly Known As Sugam Polytech Pvt. Ltd.)

Plot No. 106, G.I.D.C. Bamanbore, Old NH 8B, Tal.: Chotila,
Dist.: Surendranagar, (Guj.) INDIA. Pin : 363 520.
☎ +91 98791 56783
✉ info@hasonchem.com 🌐 www.hasonchem.com