



Product Name	:	Estergum (Pentaerythritol Base)
Softening Point (Ring & Ball Method)	:	105-106°C
Melting Point (Capillary Method)	:	95 - 100°C
Acid Value	:	17
Viscosity (50% in Toluene@ 30°C)	:	15 Secs.(In B4 Cup)
Colour Gardner	:	6
Tolerance	:	1 : Infinite in MTO (BPCL)

146, Dadar Gally, M. J. Market, Zaveri Bazar, Mumbai - 400 002.

Tel. : 2240 8088 | Telefax : 2240 8089 | E-mail : dyconchemicals@gmail.com | nishit@dyconchemicals.com | Website : www.dyconchemicals.com