

## Globalprene 3411

## Styrene-Butadiene block copolymer 苯乙烯-丁二烯嵌段共聚合物

Typical Properties	Test Method	Unit	Typical Value	Range
一般性質	測試方法	單位	數值	數值
Styrene content 苯乙烯含量	ASTM D5775	%	30	29.5~32.5
Specific Gravity 比重	ASTM D792	g/cc	0.94	N/A
Volatile Matter 揮發份	ASTM D5668	%	0.25	≤0.5
Ash Content 灰份	ASTM D5667	%	0.3	≤1.0
Molecular Weight 分子量	ASTM D5296	Daltons	240K	235K~255K

Packing 包裝 :	12kg paper bag	12 公斤紙袋
	15kg paper bag	15 公斤紙袋
	400kg super bag	400 公斤太空袋
	450kg super bag	450 公斤太空袋
	408.2kg super bag	408.2 公斤太空袋

All ingredients in the product are in compliance with the following chemical inventories:

United States: Toxics Substances Control Act Inventory (TSCA)

Europe: European Inventory of Existing Chemical Substances (EINECS)

Canada: Canadian Domestic/ Non-Domestic Substances List (DSL)

Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

Australia: Australian Inventory of Chemical Substances

Korea: Korean Existing Chemicals List (KECL)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

EU Directive 2002/95/EC RoHS (Restriction of certain Hazardous Substances)

EC No 1907/2006 SVHC (Substances of Very High Concern)

CEN Standard EN71.3

Organo-tin Compounds

### Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

Head office 總公司 台北市八德路四段 83 號 3 樓  
3F, No.83, Sec. 4, Bade Road, Taipei 105, Taiwan

Tel : 886-2-2763-1611  
Fax : 886-2-27645749

USA office 美國 4903 Decker Drive Baytown, Texas 77520, USA

Tel : 1-281-424-6100  
Fax : 1-281-424-6169