



## GLOBALPRENE 3501

### TECHNICAL DATA SHEET / SALES SPECIFICATION

Styrene - Butadiene block copolymer specially designed for asphalt modification, compounding and for solvent based adhesive applications.

### TYPICAL POLYMER COMPOSITION

Molecular Structure	Linear
Styrene Content	30% By weight
Butadiene Content	70% By weight
Physical Form	Porous Pellet

### SPECIFICATION

<u>Polymer Properties</u>	<u>Unit Measure</u>	<u>Typical Value</u>	<u>Range</u>	<u>Test Method</u>	<u>Referred Standard</u>
Specific Gravity	g/cc	0.94	N/A		ASTM D 792
Volatile Matter	%	0.17	1.0 max	BP 70	ASTM D 5668
Ash Content	%	0.11	1.0 max	BP 8	ASTM D 5667
Bound Styrene	%	32	30 - 34	BP 10	-
Coupling Efficiency	%	90	84 min	BP 540	ASTM D 5296
Brookfield Viscosity (A)	cps	5400	4300-6200	BP 705	ASTM D 2196

#### A. Toluene solution, total solids content 25% by weight at temperature of 23°C

The information and data presented herein are, to the best of our knowledge, true and accurate. They are intended for use by persons having technical skill and at their own discretion and risk; no warranty or guarantee, expressed or implied, is made and no liability is assumed in connection with any use of such information and data. Nothing herein shall be construed as a recommendation to infringe any existing patents or violate any applicable laws.