

 **YUEN LIANG INDUSTRIAL & CO., LTD. TAIWAN**

Technical Data Sheet

AR-E100A
Hydrocarbon resin

Hydrocarbon resin AR-E100A is a low molecular weight, pale yellow thermoplastic resin, produced from petroleum-derived monomers. 碳氫樹脂 AR-E100A 是一種低分子量，淡黃色的熱塑性樹脂，由石油衍生的單體製成。

SPECIFICATIONS 產品規格

Softening Point (Ring & Ball), °C 軟化點	100 ± 5	ASTM E28
Color (Gardner), 50wt% in Toluene 顏色	6 Max.	ASTM D1544
Bromine Number, Br cg/g 溴價	25 Max.	ASTM D1159
Acid Number, KOH mg/g 酸價	0.1 Max.	ASTM D664
Specific Gravity, @25°C 比重	1.03 ~ 1.10	ASTM D71

APPLICATIONS 應用

Adhesives and Hot Melt 黏膠, 熱熔膠

Rubber 橡膠

EXAMPLES 應用產品

Woodworking Hot Melt 木工熱熔膠

Packaging Adhesive 包裝材料用黏劑

HMPSA 感壓熱熔膠

Adhesive Solvent Base 溶劑型黏膠

Tires, Shoe 環保高性能輪胎, 鞋材

All information showed in this data sheet is based on careful examinations and investigations. We cannot assume any responsibility in connection with the individual use of our products, nor do we warrant against any loss or damages directly caused by the individual use of our products.

PACKAGING 包裝

25 kgs PE woven cloth laminated with kraft paper bag, 500 kgs jumbo bag

25 公斤 PE 編織淋膜牛皮紙袋, 500 公斤太空袋

STORAGE 儲存

Indoor storage is strongly recommended. 強烈建議室內儲存

Storage at temperatures above 30°C should be avoided. 應避免儲存溫度高於 30°C

146, Dadar Gally, M. J. Market, Zaveri Bazar, Mumbai - 400 002.

Tel. : 2240 8088 | Telefax : 2240 8089 | E-mail : dyconchemicals@gmail.com | nishit@dyconchemicals.com | Website : www.dyconchemicals.com