

OK Flux 10.81LHS

Agglomerated aluminate-basic flux for Submerged Arc Welding. General purpose flux specially designed for fillet welding applications at high speeds primarily with single & twin wire systems for all carbon steels operated in DC. Further attributes include very good surface finish, slag detachability, concave horizontal fillets & uniform toe wetting. Major applications include pre-engineered buildings (PEB's), general construction etc.

Classifications	EN ISO 14174 : S A AB 1 77 DC
------------------------	-------------------------------

Slag Type	Aluminate-basic
Alloy Transfer	Silicon and Manganese alloying
Density	nom 1.3 kg/dm ³

Classifications

Wire	SFA/AWS - EN ISO	AWS - As Welded
OK Autrod 12.22L	A5.17:EM12K/ 14171-B:SU21	A5.17: F7A2-EM12K

Typical Mechanical Properties

Combined with Wire	Condition	Yield Strength	Tensile Strength	Elongation	Charpy V-Notch
OK Autrod 12.22L	As Welded DC+	460 MPa	540 MPa	30 %	80 J @ -18°C 50 J @ -29°C

Typical Weld Metal Analysis %

C	Mn	Si
OK Autrod 12.22L DC+ 550A, 29V		
0.06	1.90	0.70